



Anti-reflective film of photovoltaic cell, has columnar elements having maximum wavelength below light, that is formed over light injection region of photoelectric conversion element, for converting light energy into electric energy

Kazuaki, Sasaki; Atsushi, Yoshida; Tatsuya, Takamoto; Akio, Higo; Masakazu, Sugiyama; Masanori, Kobota; Yoshiaki, Nakano; Pastorelli, Francesco; Kentaro, Watanaabe

Publication date:
2011

Document Version
Publisher's PDF, also known as Version of record

[Link back to DTU Orbit](#)

Citation (APA):
Kazuaki, S., Atsushi, Y., Tatsuya, T., Akio, H., Masakazu, S., Masanori, K., Yoshiaki, N., Pastorelli, F., & Kentaro, W. (2011). Anti-reflective film of photovoltaic cell, has columnar elements having maximum wavelength below light, that is formed over light injection region of photoelectric conversion element, for converting light energy into electric energy.

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

**Espacenet****Bibliographic data: JP2011119740 (A) — 2011-06-16**

ANTIREFLECTION FILM, SOLAR BATTERY CELL, METHOD FOR MANUFACTURING ANTIREFLECTION FILM, AND METHOD FOR MANUFACTURING SOLAR BATTERY CELL

Inventor(s): SASAKI KAZUAKI; YOSHIDA ATSUSHI; TAKAMOTO TATSUYA; HIGO AKIO; SUGIYAMA MASAKAZU; KUBOTA MASANORI; NAKANO YOSHIKI; FRANCESCO PASTORELLI; WATANABE KENTARO ± (SASAKI KAZUAKI, ; YOSHIDA ATSUSHI, ; TAKAMOTO TATSUYA, ; HIGO AKIO, ; SUGIYAMA MASAKAZU, ; KUBOTA MASANORI, ; NAKANO YOSHIKI, ; FRANCESCO PASTORELLI, ; WATANABE KENTARO)

Applicant(s): SHARP KK; UNIV TOKYO ± (SHARP CORP, ; UNIV OF TOKYO)

Classification: - international: ***H01L31/04***
- cooperative: **Y02E10/544**

Application number: JP20100270658 20101203

Priority number(s): US20090266651 20091204

Abstract of JP2011119740 (A)

PROBLEM TO BE SOLVED: To provide a multilayer antireflection film achieving low reflectance over a wide band and a wide incident angle range. ; SOLUTION: An antireflection film 10 is composed of a plurality of dielectric layers (11, 12) laminated on the light receiving surface of a photoelectric conversion element 30. In at least one layer of the plurality of dielectric layers, microstructures (columnar bodies 15) are formed over a region which light enters, wherein a width in the longitudinal direction of each microstructure is equal to or less than the maximum wavelength of the light converted into electricity by the photoelectric conversion element. ; COPYRIGHT: (C)2011,JPO&INPIT